

PolyGen HAO.218-2 LLDPE



Product Description

Linear Low Density Polyethylene – Higher Alpha Olefin Copolymer – Film Resin

Additive Package = Antiblock

Properties	Property Value	Test Method
Melt Index (g/10 min)	2.2	ASTM D1238
Density (g/cm ³)	0.919	ASTM D792
Film Thickness - Tested	1.0 mil	
Film Toughness		ASTM D882
MD : 0.80 mil	2050 ft/lb in ³	
TD : 0.80 mil	1900 ft/lb in ³	
Tensile Strength		ASTM D882A
MD : Break, 1.0 mil	6900psi	
TD : Break, 1.0 mil	4000psi	
Elmendorf Tear Strength		ASTM D1922
MD	310g	
TD	485g	
Dart Drop Impact (1.0 mil)	195g	ASTM D1709A
Haze	0.35%	ASTM D1003

* These average values were obtained from specimens molded under carefully controlled laboratory conditions. This data should be used only as a guide and no assurance can be granted by the company that all molded articles will exhibit duplicate properties at those listed above.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described wherein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.

shawpolymers.com



CORPORATE HEADQUARTERS

400 N. Indiana Ave.
Crown Point, IN 46307